



S135 - Blending Additive

Description:


- For Blending-in Gen2O Waterbourne Basecoat.
- Easy handling.
- Ready to spray.

Application 1:

Blending-in Gen2O Basecoat directly over S135 Blending agent.



- Mix S135. 5:1 with Gen2o water S120.
- Spray blending area with one coat of S135 avoiding the edges
- Apply mixed Gen2o Basecoat in the wet film until covered.
- Blend-in the overlapping area with reduced air pressure (1.0-1.5 bar)




General Clearcoats.

Application 2:

Blending-in Gen2o Basecoat mixed with S135 Blending agent.



- Mix Gen2o Basecoat with 50% S135 blending agent.
- Blend-in overlapping area with reduced air pressure by (1.0 – 1.5 bar)



General Clearcoats.

Product Data Sheet



S135 - Blending Additive

Note:

Occasionally it may be necessary to obtain opacity on the primed area before proceeding.

Cleaning the Equipment:

Clean after use with Water.

Safety:

Refer to Material Safety Data Sheet (MSDS) for complete safety instructions. The technical data sheet listed has been compiled in good faith for your convenience and guidance. No warranty, expressed or implied, is intended or given by the information on this sheet.

Note: General recommends that our products not be used under 10°C. Usage below 10°C can result in extended drying times or product failure.

Product Data Sheet